

Σωλήνες Vacupress Cristal FDA VACUPRESS CRISTAL FDA

Manufacturer: Continental/Merlett




Σωλήνας δύο στρώσεων από μαλακό PVC, εγκεκριμένος για τρόφιμα, με ενσωματωμένο σπирάλ από γαλβανισμένο χάλυβα με ενίσχυση από πολυεστερικό νήμα, για αναρρόφηση και παροχή στερεών και υγρών, καθώς και τροφίμων.

Manufacturer's notices

The details given are purely indicative.

It is the responsibility of the user to establish if the product is suitable for his purpose.

At Continental, our aim is to ensure that the purchaser/user does so with the confidence that our production is constantly monitored and checked for compliance to the certifications obtained and as published in our current sales catalogues and our data sheets.



Σωλήνες Vacupress Cristal FDA

VACUPRESS CRISTAL FDA

Manufacturer: Continental/Merlett

Technical data

NOMINAL Ø	INTERNAL Ø	EXTERNAL Ø	WEIGHT	BENDING RADIUS	WORKING PRESS.	BURSTING PRESS.	VACUUM	COIL LENGTH
mm	mm	mm	g/m	mm	bar	bar	m H ₂ O	m
19	19	28	450	80	20	60	9	60
25	25	35,5	670	90	20	60	9	60
30	30	40,5	770	105	16	48	9	60
32	32	42,5	800	110	16	48	9	60
35	35	47	1100	125	14	42	9	60
38	38	51	1150	135	14	42	9	30
40	40	53,5	1200	140	14	42	9	30
45	45	58	1400	155	14	42	9	30
50	50	63,5	1600	170	14	42	9	30
60	60	74	1980	200	12	36	9	30
63	63	77	2050	210	12	36	9	30
70	70	85,5	2550	240	12	36	9	30
76	76	92	2800	250	12	36	9	30
80	80	96	2850	300	10	30	9	30
90	90	106,5	3300	350	10	30	9	30
102	102	119	3900	400	10	30	9	30
120	120	138	4800	480	8	24	9	20
127	127	145	5200	500	7	21	9	20
152	152	171	6700	600	5	15	9	20

Measurements and operating data are not legally binding and subject to change without notice.

Other specifications

	SMOOTH SURFACE	*****
	FLEXIBILITY	***
	ABRASION RESISTANCE	***
	TEMPERATURE RANGE	-5 °C + 65 °C
	CHEMICAL RESISTANCE	PVC CHART
	CRUSHING RESISTANCE	***
	O-PHTHALATE FREE	PHF *****
	SUITABLE FOR FOOD CONTACT APPLICATIONS ACCORDING TO EU/FDA REGULATIONS - SEE DECLARATION OF CONFORMITY	